



MUSEUM NATIONAL D'HISTOIRE NATURELLE
DEPARTEMENT : REGULATIONS,
DEVELOPPEMENT

ET DIVERSITE MOLECULAIRE
UMR 7245 CNRS / MNHN
PROTECTION DES MATERIAUX

case 39, 12, rue Buffon 75005
Tél. : 01 4079 3208/3195 - Fax : 01 4079 3594 - E-mail : yep@mnhn.fr



Paris, January 08, 2015

V/Ref : your order n° 4400480523 for a fungal test delivered on November 07, 2014

N/Ref : CY PV N° 20161 3 B

FUNGUS RESISTANCE TEST OF A SAMPLE
FROM EUROCOUSTIC COMPANY

Tests were performed according to the specifications of the standard NF EN ISO 846, method B.

Incubation time: 28 days,

Fungal strains: *Aspergillus niger* : DSM 1957

Penicillium funiculosum : DSM 1944

Paecilomyces variotii : DSM 1961

Gliocladium virens : DSM 1963

Chaetomium globosum : DSM 1962

Product Reference: Tonga® Ultra Clean A 22

RESULTS

Method B: Fungistatic effect test

Painted upper side

At the end of the test incubation, no fungal growth was observed on the test surface, **grade 0**, complete fungistatic effect.

Claude YÉPRÉMIAN
Responsable Sce Protection des Matériaux